



PRODUCT DESCRIPTION

Sterlite® OH-LITE® Single Mode Optical Fiber is a low water peak fiber where attenuation at 1380-1390 nm is less than attenuation at 1310 nm.

PRODUCT APPLICATION

Sterlite® OH-LITE® is ideal for regional, metropolitan and local access networks using CWDM.

PRODUCT BENEFITS

Sterlite® OH-LITE® single mode fiber is designed for use over the entire 1260 nm to 1625 nm wavelength range. This gives it much more useable spectrum than conventional single mode fiber.

PRODUCT SPECIFICATIONS

Attenuation	≤ 0.34 dB/km at 1310 nm < 0.34 dB/km at 1383 nm or less than attenuation at 1310 nm# ≤ 0.20 dB/km at 1550 nm ≤ 0.23 dB/km at 1625 nm
Mode field diameter	9.2 ± 0.4 μ m at 1310 nm 10.4 ± 0.5 μ m at 1550 nm
Cabled cutoff wavelength	≤ 1250 nm
Zero dispersion wavelength	1304 nm to 1322 nm
Zero dispersion slope	≤ 0.090 ps/nm ² .km
Dispersion at 1550 nm	≤ 17.5 ps/nm.km
Fiber polarization mode dispersion link design value*	≤ 0.2 ps/ \sqrt km
Cladding diameter	125.0 ± 0.7 μ m
Core-clad concentricity error	≤ 0.5 μ m
Cladding non-circularity	≤ 0.8 %
Coating diameter (uncolored)	245 ± 5 μ m
Coating-cladding concentricity error	≤ 8 μ m

* Individual PMD values may change when cabled # After hydrogen aging according to IEC-60793-2-50 regarding the B1.3 fiber category

MECHANICAL CHARACTERISTICS

Proof test levels	100 kpsi (0.7 GN/m ²). This is equivalent to 1% strain	
Coating strip force (Force to mechanically strip the dual coating)	≥ 1.3 N (0.3 lbf) and ≤ 5.0 N (1.2 lbf)	
Fiber curl	≥ 4 m	
Macrobend loss: The maximum attenuation with bending does not exceed the specified values with the following deployment conditions		
Deployment condition	Wavelength	Induced attenuation
1 turn, 16 mm (0.6 inch) radius	1550 nm	≤ 0.50 dB
100 turns, 30 mm (1.18 inch) radius	1625 nm	≤ 0.10 dB
	1550 nm	≤ 0.05 dB

ENVIRONMENTAL CHARACTERISTICS

Temperature dependence Induced attenuation, -60 °C to +85 °C at 1310 & 1550 nm	≤ 0.05 dB/km
Temperature humidity cycling Induced attenuation, -10 °C to +85 °C and 95% relative humidity at 1310 & 1550 nm	≤ 0.05 dB/km
High temperature and humidity aging 85 °C at 85% RH, 30 days Induced attenuation at 1310 & 1550 nm due to aging	≤ 0.05 dB/km
Water immersion, 30 days Induced attenuation due to water immersion at 23±2 °C at 1310 & 1550 nm	≤ 0.05 dB/km
Accelerated aging (Temperature), 30 days Induced attenuation due to temperature aging at 85±2 °C at 1310 & 1550 nm	≤ 0.05 dB/km

OTHER PERFORMANCE CHARACTERISTICS*

Core diameter	8.45 μm
Effective group index of refraction	1.4670 at 1310 nm 1.4675 at 1550 nm
Attenuation in the wavelength region from 1285 - 1330 nm in reference to the attenuation at 1310 nm	≤ 0.03 dB/km
Attenuation in the wavelength region from 1525 - 1575 nm in reference to the attenuation at 1550 nm	≤ 0.03 dB/km
Point discontinuities at 1310 nm & 1550 nm	≤ 0.05 dB
Refractive index difference	0.33 %
Dynamic fatigue parameter (Nd)	≥20
Weight per unit length	64 gm/km

*Typical value

LENGTH & SHIPPING DETAILS

Shipping spool flange diameter	23.50 cm (9.25 inches) or 26.5 cm (10.4 inches)
Shipping spool barrel diameter	15.24 cm (6.0 inches) or 17.0 cm (6.7 inches)
Shipping spool traverse width	9.55 cm (3.76 inches) or 15.0 cm (5.9 inches)
Shipping spool weight	0.50 kg (1.36 lbs) or 0.88 kg (1.93 lbs)
Shipping length: standard length per reel available up to 25.2 km. lengths per reel as per customer request are also available	

MANUFACTURING PROCESS

Sterlite® controls every stage of the manufacturing process so that quality is built in to every meter of fiber, rather than selected out at the end through testing. To ensure the accuracy and precision of the manufacturing process, Sterlite routinely calibrates and recertifies process equipment and measurement benches against internationally traceable standards from NPL/NIST, and follow test methods compliant with EIA/TIA, CEI-IEC and ITU standards.

INTERNATIONAL STANDARDS

Sterlite® OH-LITE® complies with or exceeds ITU recommendation G.652.C/D and IEC 60793-2-50.

SERVICE USP'S

- Complete range of optical fiber for terrestrial networks
- World-wide sales support
- Web-based order tracking & customer support
- Specialized technical support

DISCLAIMER

Sterlite's policy of continuous improvement may result in a change in specifications without prior notice. Any warranty of any nature relating to any Sterlite product is only contained in the written agreement between Sterlite Technologies Limited and the direct purchaser of such product(s).

sterlitetechnologies.com

Aurangabad | Beijing | Campobello | Haridwar | Johannesburg | London | Moscow | Mumbai | Noida | Pune | Shanghai | Silvassa

